

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
22 January 2004 (22.01.2004)

PCT

(10) International Publication Number
WO 2004/007571 A1

(51) International Patent Classification⁷: C08F 10/00, 2/34

SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number:
PCT/GB2003/002861

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(22) International Filing Date: 3 July 2003 (03.07.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02358014.5 11 July 2002 (11.07.2002) EP

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations
- of inventorship (Rule 4.17(iv)) for US only

(71) Applicant (*for all designated States except US*): BP
CHEMICALS LIMITED [GB/GB]; Britannic House, 1
Finsbury Circus, London EC2M 7BA (GB).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **ISNARD,**
Jean-Pierre [FR/FR]; 3, allée Tiboulen, Les Bastides
II, F-13960 Sausset-les-Pins (FR). **SITRUCK, Claude**
[FR/FR]; 9, allée des Vigniero, F-13500 Martigues (FR).

(74) Agent: **PREECE, Michael**; BP International Lim-
ited, Patents and Agreements, Chertsey Road, Sun-
bury-on-Thames, Middlesex TW16 7LN (GB).

Published:

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,

(54) Title: PROCESS FOR THE (CO-)POLYMERISATION OF OLEFINS IN THE GAS PHASE

(57) Abstract: Process for the polymerisation or copolymerisation in the gas phase of olefin(s) by bringing the said olefin(s) into contact, under polymerisation or copolymerisation conditions in a reactor in which the polymer or the copolymer is maintained in a fluidized bed and/or agitated with mechanical stirring, with a catalyst system, which process comprises a pre start-up operation characterized in that, prior to the introduction of the catalytic system in the reactor, the reactor is subjected to a cleaning treatment comprising the steps of introducing into the reactor an alkane having from 4 to 8 carbon atoms, circulating said alkane across the reactor under pressure and elevated temperature, depressurizing and purging the reactor.

PROCESS FOR THE (CO-)POLYMERISATION OF OLEFINS IN THE GAS
PHASE

The present invention relates to a process for improving the start up of polymerization or copolymerization of alpha-olefins in a gas phase reactor, preferably a fluidized bed gas phase reactor.

Polymerizing alpha-olefins in the gas phase by bringing them into contact with a catalyst system in an apparatus comprising, for example, a reactor with a fluidized bed and/or with mechanical stirring is known. In the special case of the use of a fluidized bed reactor, the solid polymer in course of formation is kept in the fluidized state by means of a rising reaction gas mixture, comprising the alpha-olefins to be polymerized. This gaseous mixture leaving the reactor is generally cooled before being recycled into the reactor and an additional quantity of alpha-olefins corresponding to the quantities consumed is added to it. The start up of the polymerization reaction in the gas phase is generally performed by introducing the catalyst system into a reactor fed with reaction gas mixture, and also containing a charge powder. This charge powder, consisting of solid particles, such as particles of polyolefin, is used to form the initial bed at the moment when the polymerization reaction starts up, favoring in particular a suitable dispersion of the catalyst system in the reaction medium. Polymerization may then be performed continuously, the catalyst system being introduced into the reactor continuously or in sequence. The polymer produced may be withdrawn from the reactor also continuously or in sequence.

In the industrial production of polyolefins, it may be necessary to stop the polymerization reaction temporarily in order to be able to carry out various operations for maintaining or cleaning the reactor. Impurities such as water and oxygen may be introduced during these various operations into the polymerization apparatus and/or into

the charge powder introduced into the reactor when the reaction is restarted. Under these conditions and although the catalyst system used, of Ziegler-Natta type, is known for not having an induction period, the polymerization reaction commences several hours after the commencement of introduction of the catalyst system into the reactor.

5 The actual start up of polymerization consequently takes place in the presence of a relatively high concentration of catalyst system in the fluidized bed, so that the polymerization reaction speed may increase rapidly and abruptly, with the risk of forming localized hot spots and the bursting of polymer grains into fine particles. These localized hot spots may lead to the formation of agglomerates and setting of the polymer
10 inside the reactor, and are liable to cause the stoppage of the polymerization reaction. Moreover, in the special case of polymerization in a fluidized bed, the fine particles, formed by the bursting of the grains making up the bed, are inevitably entrained out of this bed, which gives rise to a continuation of the polymerizing reaction outside the reactor.

15 Moreover, the considerably increased concentration of catalyst system in the fluidized bed at the moment when the reaction starts up appreciably modifies the conditions of development of the polymerization or copolymerisation, so that the polymers or copolymers produced in the initial phase of the reaction have properties notably different from those of the desired products, especially as regards density,
20 comonomer content, melt index, crystallinity and content of catalyst residues. It is then observed that it is necessary to produce a relatively high quantity of polyolefins before obtaining the product of desired quality.

 The prior art teaches to use organoaluminium compounds to purify the reactor and/or bed particles in order to improve the start-up conditions. EP180420 is an
25 example thereof.

 It has now been found that it is possible to avoid the difficulties mentioned above as well as to bring additional advantages as disclosed hereafter and to obtain the start up of the polymerization or copolymerisation reaction immediately after the alpha-olefins have been brought into contact with the catalyst system and a charge powder,
30 without the risk of formation of agglomerates or fine particles, the polyolefins produced during this period of start up having constant properties and having immediately the desired quality.

 The object of the present invention is therefore a process for the polymerisation

or copolymerisation in the gas phase of olefins by bringing the said olefins into contact, under polymerization or copolymerisation conditions in a reactor in which the polymer or the copolymer is maintained in a fluidized bed and/or agitated with mechanical stirring, with a catalyst system, which process comprises a pre start-up operation
5 characterized in that, prior to the introduction of the catalytic system in the reactor, the reactor is subjected to a cleaning treatment comprising the steps of introducing into the reactor an alkane having from 4 to 8 carbon atoms, circulating said alkane across the reactor under pressure and elevated temperature, depressurizing and purging the reactor.

The Applicants have unexpectedly found that this alkane treatment lead to
10 smooth and improved in all aspects polymerization start-ups, as showed in the examples. While not wishing to be bound to this explanation, the Applicants believe that it is the absorption capacity of the alkane which positively impacts on the polymer residues and impurities present on the reactor wall, in the piping and exchangers, so that during the depressurizing/purging steps a high desorption of these residues and
15 impurities occur by mechanical and/or dissolution and/or azeotropic type mechanisms.

The essential feature of the present invention lies in said alkane cleaning treatment of the reactor. Many different ways to proceed with this treatment can be explored by the man in the art. Hereafter are depicted some of these treatments that can advantageously be applied.

Said pre start-up operation may be performed during or preferably before or
20 after the introduction of the charge powder into the reactor. The charge powder used for the start up of polymerisation or copolymerisation consists of solid particles of an inorganic product, such as silica, alumina, talc or magnesia, or else an organic product such as a polymer or copolymer. In particular the charge powder may be a polyolefin
25 powder preferably of the same nature as that of the polyolefin powder to be produced, so that as soon as the reaction starts up, polyolefin of the desired quality is obtained immediately. Such a charge powder may in particular originate from a previous polymerisation or copolymerisation reaction. In this way one may use as charge powder a powder of a polyethylene, a polypropylene, a copolymer of ethylene with less than
30 20% by weight of one or more other alpha-olefins comprising, for example, from 3 to 12 carbon atoms, an elastomeric copolymer of ethylene with from 30 to 70% by weight of propylene, a copolymer of ethylene with less than 20% by weight of ethylene or one or more other alpha-olefins comprising from 4 to 12 carbon atoms, or a copolymer of

propylene with from 10 to 40% by weight of 1-butene or a mixture of 1-butene and ethylene. Advantageously the charge powder consists of particles having a mean diameter by mass comprised between 200 and 5000 microns, and preferably comprised between 500 and 3000 microns. The size of the charge powder particles is chosen partly
5 as a function of the size of the polyolefin particles to be produced, and partly as a function of the type of polymerisation reactor and conditions of use of this reactor, such as for example the speed of fluidisation which may for example be comprised between 2 to 10 times the minimum speed of fluidisation of the polyolefin particles to be produced.

10 The cleaning treatment consists in introducing into the reactor an alkane having from 4 to 8 carbon atoms, circulating said alkane across the reactor under pressure, depressurizing and purging the reactor.

The introduction of the alkane in a fluidised bed and/or with mechanical stirring, is preferably performed in the presence of an inert gas. In particular the treatment may
15 be performed in the presence of nitrogen. It is also preferably performed under airtight conditions in order to avoid any oxygen ingress. It is also preferably performed in the absence of reacting gas like the olefins.

For the purpose of the present description and appended claims, "under pressure" treatment means that the pressure inside the reactor is at least above the
20 atmospheric pressure. The alkane cleaning treatment is preferably carried out under a pressure comprised between 5 and 30 bars. For the purpose of the present description and appended claims, a treatment at an "elevated temperature" means that the treatment is performed at a reactor temperature of at least 40°C, preferably performed at a temperature comprised between 50 and 120°C and more preferably at a temperature
25 comprised between 70 and 110°C. Preferably, when a charge powder is present, the treatment temperature should be below the temperature at which the particles of charge powder begin to soften and form agglomerates.

The alkane is for example, butane, pentane, hexane, heptane or octane. Pentane is preferably used.

30 The quantity of alkane used according to the invention depends on the state of purity of both the reactor loop and the charge powder. Preferably, the quantity of alkane used for the treatment is such that the alkane partial pressure is comprised between 25 and 95% of the saturated vapor pressure of the said alkane under the treatment

conditions (temperature and pressure). More preferably, the quantity of alkane used for the treatment is such that the alkane partial pressure is comprised between 45 and 75% of the saturated vapor pressure of the said alkane under the treatment conditions (temperature and pressure).

5 In order to provide the most efficient cleaning treatment, it is important that this treatment should last at least five minutes and preferably over 15 minutes. It has been observed, in fact, that when the duration of the treatment is less than 5 minutes, the polymerisation or copolymerisation reaction does not start up immediately when the alpha-olefins are brought into contact with the charge powder in the presence of the catalyst system.

10 As already indicated, the cleaning process includes after the alkane circulation under pressure a depressurizing step. Then, the consecutive purge operation(s) is/are performed according to techniques in themselves known, such as successive operations of pressurising and degassing the reactor by means of gases or a mixture of gases as referred to above. They may be carried out under a pressure at least equal to atmospheric pressure, preferably under a pressure comprised between 0.1 and 5 MPa, at a temperature equal to or greater than 0 DEG C., but less than the temperature at which the charge powder particles begin to soften and form agglomerates, and preferably at a temperature comprised between 40 DEG and 120 DEG C.

20 Any appropriate additional cleaning treatment may also be performed. For example, the reactor may additionally be treated with an organoaluminium compound of the formula $AlR_n X_{3-n}$ in which R is an alkyl group comprising from 2 to 12 carbon atoms, X is a hydrogen or halogen atom, or an alcoholate group, and n is a whole number or fraction comprised between 1 and 3. Said organoaluminium additional treatment, if used, is preferably performed after the alkane treatment.

25 The organoaluminium compound, when used, may be chosen from amongst the trialkylaluminium compounds or hydrides, chlorides or alcoholates of alkylaluminium. Generally it is preferred to use a trialkylaluminium such as triethylaluminium, trisobutylaluminium, tri-n-hexyl-aluminium or tri-n-octyl aluminium. In certain cases, especially with a view to simplifying the process of the invention, the organoaluminium compound may advantageously be of the same nature as that used as co-catalyst associated with the catalyst in the catalyst system.

30 Another additional treatment could be a dehydration treatment, which essentially

consists in purge operations. If used, said additional dehydration treatment is advantageously performed before the alkane cleaning treatment of the present invention.

According to a preferred embodiment of the present invention, the cleaning treatments (purges, organoaluminum compounds and alkanes) are performed before
5 composing the reacting gas phase. Then, contacting the olefins with the charge powder in the presence of the catalytic system may be performed in a manner in itself known, by means of a polymerisation or copolymerisation reactor with a fluidized bed and/or with mechanical stirring. The reactor is fed with a reaction gas mixture consisting of 1 or more (α)-olefins and optionally hydrogen and/or one or more inert gases
10 (including additional optional alkanes), under the conditions of the polymerisation or copolymerisation reaction in the gas phase, that is to say under a pressure generally comprised between 0.1 and 5 MPa, preferably comprised between 0.5 and 4 MPa, and at a temperature generally comprised between 0 DEG and 125 DEG C., preferably comprised between 40 DEG and 120 DEG C. Finally, the catalyst is introduced into the
15 reactor and the reaction starts immediately.

Surprisingly, it has been observed that when one wishes to attain in an advantageous manner, in a relatively short time, a stable production of polyolefin of the desired quality, it is possible thanks to the process of the invention to perform the initial stage of the polymerisation or copolymerisation in the presence of the catalytic system
20 in a relatively large quantities, without forming agglomerates or fine particles.

According to the process of the invention, it is possible to polymerize or copolymerize olefins which may comprise from 2 to 12 carbon atoms, in a fluidized bed and/or with mechanical stirring under very advantageous and very simple conditions, making it possible in particular as soon as the polymerisation or copolymerisation
25 commences, to obtain polymers or copolymers of the desired quality under excellent conditions of yield and productivity of the industrial plant.

For example, using the process of the invention it is possible to produce easily high density polyethylene (density above 0.940), which include homopolymers of ethylene and copolymers of ethylene and α -olefins comprising from 3 to 12 carbon
30 atoms, linear low density polyethylene (density less than 0.940), consisting of a copolymer of ethylene and 1 or more α -olefins comprising from 3 to 12 carbon atoms, with a content by weight of units derived from ethylene of over 80%, elastomeric terpolymers of ethylene, propylene and dienes, elastomeric copolymers of ethylene and

propylene, having a content by weight of units derived from ethylene comprised between about 30 and 70%, isotactic polypropylene and copolymers of propylene and ethylene or other alpha-olefins, having a content by weight of units derived from propylene of over 90%, copolymers of propylene, 1-butene and optionally ethylene
5 having a content by weight of units derived from 1-butene and optionally ethylene comprised between 10 and 40% .

Example

The gas phase fluidised bed reactor equipment used corresponds to the one disclosed in figure 3 of WO9428032. It has an internal diameter of the cylinder of 0.75
10 m and a height of the cylinder of 6 m.

The reactor is purged with nitrogen at 90°C by proceeding with three consecutive pressurizing (16 bars) – depressurizing (1 bar) steps in order to end with a water content of less than 5 ppm, and preferably less than 2 ppm in nitrogen in the reactor.

15 The start-up powder (an HDPE or LLDPE polymer) is introduced into the reactor and fluidized with nitrogen. If the measured water content in nitrogen is less than 2 ppm, which is synonymous of an unpolluted bed – no additional water purge is thus necessary (optional step). If the water content is above 2 ppm, it is better to swing pressure until the 2 ppm level is reached.

20 Pentane is then introduced into the reactor so that its partial pressure in the reactor is 2.5 bars. Fluidisation is continued for half an hour under conditions of 15 bars of total pressure and 88°C.

The reactor is then purged with nitrogen at 88°C by proceeding with five consecutive pressurizing (16 bars) – depressurizing (1 bar) steps.

25 The reaction gas mixture is then composed and the catalyst introduced into the reactor.

The polymerization reaction starts immediately / no agglomerates or fine particles are formed / and the polyolefins produced during this period of start up have constant properties and the desired quality.

Claims:

1. Process for the polymerisation or copolymerisation in the gas phase of olefin(s) by bringing the said olefin(s) into contact, under polymerization or copolymerisation conditions in a reactor in which the polymer or the copolymer is maintained in a fluidized bed and/or agitated with mechanical stirring, with a catalyst system, which process comprises a pre start-up operation characterized in that, prior to the introduction of the catalytic system in the reactor, the reactor is subjected to a cleaning treatment comprising the steps of introducing into the reactor an alkane having from 4 to 8 carbon atoms, circulating said alkane across the reactor under pressure and elevated temperature, depressurizing and purging the reactor.
2. Process according to claim 1 wherein the reactor contains a charge powder and wherein said cleaning treatment is performed before, after or during the introduction of the charge powder into the reactor.
3. Process according to claim 2 wherein said cleaning treatment is performed before introduction of the charge powder into the reactor.
4. Process according to any of the preceding claims wherein the introduction of the alkane is performed in the presence of an inert gas, e.g. nitrogen.
5. Process according to any of the preceding claims wherein the cleaning treatment is performed under airtight conditions, in the absence of reacting gas like the olefins.
6. Process according to any of the preceding claims wherein the cleaning treatment comprises circulating the alkane across the reactor under a pressure above the atmospheric pressure, preferably comprised between 5 and 30 bars.
7. Process according to any of the preceding claims wherein the cleaning treatment comprises circulating the alkane across the reactor at a temperature of at least 40°C,

preferably at a temperature comprised between 50 and 120°C.

8. Process according to any of the preceding claims wherein the alkane is chosen amongst one or more of butane, pentane, hexane, heptane or octane.

9. Process according to claim 8 wherein pentane is used as the alkane.

5 10. Process according to any of the preceding claims wherein the quantity of alkane used for the treatment is such that the alkane partial pressure is comprised between 25 and 95% of the saturated vapor pressure of the said alkane under the temperature and pressure treatment conditions.

11. Process according to claim 10 wherein the quantity of alkane used for the
10 treatment is such that the alkane partial pressure is comprised between 45 and 75% of the saturated vapor pressure of the said alkane under the treatment conditions.

12. Process according to any of the preceding claims wherein the treatment last at least five minutes and preferably over 15 minutes.

15

20

25

30

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/02861

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F10/00 C08F2/34

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 853 091 A (BP CHEMICALS SNC) 15 July 1998 (1998-07-15) claims	1,2,4, 6-12
A	EP 0 180 420 A (BP CHEM INT LTD) 7 May 1986 (1986-05-07) cited in the application claims	1-12
A	EP 0 722 956 A (HOECHST AG) 24 July 1996 (1996-07-24) page 9, line 17 - line 21; claims	1
A	EP 0 574 821 A (SPHERILENE SRL ;HIMONT INC (US)) 22 December 1993 (1993-12-22) page 6, line 17 - line 28; claims 1,4-6	1-12
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the International filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the International filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *Z* document member of the same patent family

Date of the actual completion of the International search

16 September 2003

Date of mailing of the International search report

26/09/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Kaumann, E

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/02861

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 026 502 A (LOGSDON PETER B ET AL) 25 June 1991 (1991-06-25) column 1, line 60 -column 5, line 10; claims	1-12
A	----- PATENT ABSTRACTS OF JAPAN vol. 016, no. 265 (C-0951), 16 June 1992 (1992-06-16) & JP 04 063290 A (ASAHI CHEM IND CO LTD), 28 February 1992 (1992-02-28) abstract	1-12
A	----- US 6 162 779 A (MARTIN JEAN-JACQUES ET AL) 19 December 2000 (2000-12-19) claims	1,10,12
A	----- US 3 477 513 A (FERGUSON JAMES D) 11 November 1969 (1969-11-11) claims	1-12
P,X	----- WO 03 033550 A (OSMONT ERIC ;BP LAVERA S N C (FR); HESLOP DAVID (FR); BP CHEM INT) 24 April 2003 (2003-04-24) page 7, line 1 - line 11	1-12
P,X	----- WO 03 016362 A (NICASY RUDDY ;SCHOUTERDEN PATRICK J (NL); GEMOETS FREDERIK E (NL);) 27 February 2003 (2003-02-27) page 10, line 21 -page 11, line 16	1-12

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 03/02861

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0853091	A	15-07-1998	EP 0853091 A1	15-07-1998
			AU 747055 B2	09-05-2002
			AU 5565798 A	03-08-1998
			BR 9806744 A	14-03-2000
			CN 1249762 T	05-04-2000
			EG 22048 A	30-06-2002
			EP 0952993 A1	03-11-1999
			WO 9830605 A1	16-07-1998
			HU 0000776 A2	28-07-2000
			JP 2001508098 T	19-06-2001
			NO 993432 A	13-09-1999
			NZ 336639 A	30-11-2001
			PL 334549 A1	13-03-2000
			SK 93699 A3	16-05-2000
			TR 9901588 T2	21-09-1999
			US 6437062 B1	20-08-2002
			ZA 9800225 A	12-07-1999
EP 0180420	A	07-05-1986	FR 2572083 A1	25-04-1986
			CA 1265646 A1	06-02-1990
			DE 3574386 D1	28-12-1989
			EP 0180420 A1	07-05-1986
			IN 165764 A1	06-01-1990
			JP 7084484 B	13-09-1995
			JP 61123607 A	11-06-1986
			SG 48392 G	19-02-1993
			US 5077358 A	31-12-1991
EP 0722956	A	24-07-1996	AU 640288 B2	19-08-1993
			AU 8776191 A	14-05-1992
			CA 2055220 A1	13-05-1992
			DE 59108100 D1	26-09-1996
			DE 59109217 D1	20-09-2001
			EP 0485820 A2	20-05-1992
			EP 0722956 A2	24-07-1996
			ES 2093058 T3	16-12-1996
			ES 2162953 T3	16-01-2002
			JP 3143174 B2	07-03-2001
			JP 4268308 A	24-09-1992
			JP 11209420 A	03-08-1999
			US 5239022 A	24-08-1993
			ZA 9108924 A	29-07-1992
EP 0574821	A	22-12-1993	IT 1262948 B	22-07-1996
			IT 1262951 B	22-07-1996
			AT 163946 T	15-03-1998
			AU 4132093 A	23-12-1993
			BR 9302394 A	11-01-1994
			CA 2098762 A1	19-12-1993
			CN 1083491 A , B	09-03-1994
			DE 69317331 D1	16-04-1998
			DE 69317331 T2	15-10-1998
			EP 0574821 A2	22-12-1993
			ES 2114969 T3	16-06-1998
			FI 932803 A	19-12-1993
			JP 3354989 B2	09-12-2002
			JP 6100623 A	12-04-1994
			NO 932239 A	20-12-1993

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 03/02861

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0574821	A		RU 2126015 C1 US 5728353 A	10-02-1999 17-03-1998
US 5026502	A	25-06-1991	NONE	
JP 04063290	A	28-02-1992	NONE	
US 6162779	A	19-12-2000	FR 2733248 A1 AT 190093 T AU 702084 B2 AU 5653596 A BR 9608047 A CA 2216820 A1 CN 1187847 A ,B DE 69606859 D1 DE 69606859 T2 EP 0821725 A1 ES 2144741 T3 WO 9633261 A1 JP 11503782 T NO 974801 A PL 322869 A1 RU 2126442 C1	25-10-1996 15-03-2000 11-02-1999 07-11-1996 26-01-1999 24-10-1996 15-07-1998 06-04-2000 05-10-2000 04-02-1998 16-06-2000 24-10-1996 30-03-1999 17-10-1997 02-03-1998 20-02-1999
US 3477513	A	11-11-1969	NONE	
WO 03033550	A	24-04-2003	WO 03033550 A1	24-04-2003
WO 03016362	A	27-02-2003	WO 03016362 A1	27-02-2003